



47
YEARS
OF KNOW-HOW

FIBER MASTERBATCHES

monoconcentrates for spin colouration of polyolefin staple, fiber, multifilament textile products and woven raffia

PRODUCT CODE	COLOUR INDEX	PIGMENT CONT. %	HEAT STABILITY °C	LIGHT FASTNESS	MIGRATION
White PE 15050 / AT	P.White 6	50	280	7/8	5
White PE 16040 / AT	P.White 6	60	280	7/8	5
White PE 17030 / AT	P.White 6	70	280	7/8	5
Yellow PE 61 / C	P.Yellow 13	25	240	4/5	5
Yellow PE 66 / C	P.Yellow 13	40	240	4/5	5
Yellow PE 62 / C	P.Yellow 17	25	230	6/7	5
Yellow PE 67 / C	P.Yellow 17	40	230	6/7	5
Yellow PE 42 / C	P.Yellow 139	40	230	6/7	5
Yellow PE 52 / C	P.Yellow 83	20	260	6/7	5
Yellow PE 43 / C	P.Yellow 83	40	260	6/7	5
Yellow PE 49 / C	P.Yellow 34	40	260	6/7	5
Yellow PE 50 / C	P.Yellow 34	50	260	6/7	5
Orange red PE KA 1-N	P.Red 104	40	260	6/7	5
Orange red PE KA 4	P.Red 104	60	260	6/7	5
Red PE K	P.Red 48 :2	40	260	5	5
Red PE KC 6	P.Red 48 :3	20	260	5	5
Red PE KC 3	P.Red 48 :3	40	260	5	5
Red PE KC 1	P.Red 53 :1	20	270	4	5
Red PE KC 2	P.Red 53 :1	25	270	4	5
Red PE KC 7	P.Red 53 :1	40	270	4	5
Red PEK 5	P.Red 57 :1	25	260	4	5
Dark red PE KC 4	P.Red 101	50	280	8	5
Red PE KC 5	P.Red 170	40	260	7	5
Blue PE 30846/C2	P.Blue 15 :1	25	260	8	5
Blue PE 30846/DS	P.Blue 15 :1	30	260	8	5
Blue PE 30846/D	P.Blue 15 :1	40	260	8	5
Blue PE 30846/DB1	P.Blue 15 :3	30	260	8	5
Blue PE 30846/DB	P.Blue 15 :3	40	260	8	5
Blue PE 30846/CO	P.Blue 29	50	280	8	5
Blue PE 30846/CV	P.Violet 15	50	280	8	5
Green PE G	P.Green 7	40	280	8	5
Green PE G5	P.Green 7	50	280	8	5
Black PE 23070 / AT-S	P.Black 7	30	280	8	5
Black PE 24060 / AT-S	P.Black 7	40	280	8	5